

Chemical reaction anchors VBA-Z

type MKT chemical reaction anchor VZ

Features




Temperature in borehole [°C]	Min. hardening time
-20 to -16	17 h
-15 to -11	7 h
-10 to -6	4 h
-5 to -1	3 h
0 to +4	50 min
+5 to +9	25 min
+10 to +19	15 min
+20 to +29	6 min
+30 to +40	

Cartridge temperature during processing -15 °C to +40 °C

Steel wire brushes

for chemical reaction anchors VBA-Z

Suitable for	Diameter [mm]	Size	Part no.	Sales unit	Pack unit
10 mm borehole	11	M8	135571	1	Pieces
12 mm borehole	13	M10	135572		
14 mm borehole	16	M12	135573		
18 mm borehole	20	M16	135574		



The load-bearing capability of the plug at all frictional and chemical plug and anchor connections is influenced decisively by the cleanliness of the drilled hole. Residues such as drill dust reduce the effectiveness of the connection. For this reason, blow or brush out the hole with the steel wire brush to free it from dust before inserting the mortar cartridges and anchor rods.

